



MT. SAVAGE SPECIALTY REFRATORIES COMPANY

736 WEST INGOMAR ROAD · INGOMAR, PA 15127 · (412) 367-9100 · WWW.MTSAVAGE.COM

DELTA t CRETE Insulating Castables & Gun Mixes

Mt. Savage Specialty Refractories carries the most complete and versatile line of lightweight insulating castables and gun mixes in the industry. Products with temperature ratings from 1600°F to 3300°F and densities from 25 to 98 lbs/ft³ ensure that Mt. Savage has right insulating castable to improve the operating efficiency and safety for your most demanding high temperature applications.

	Max Service Temperature	Density, lbs/ft ³	Thermal Conductivity, BTU/ft ² /hr/°F/in		
			@ 500 F	@ 1000 F	@ 1500 F
DELTA t CRETE BLOCK MIX	1600°F	25	0.51	0.73	--
DELTA t CRETE 18	1800°F	52	1.3	1.4	1.6
DELTA t CRETE 20-35	2000°F	35	1.0	1.2	1.4
DELTA t CRETE 20-35 GUN MIX	2000°F	44	1.3	1.5	1.7
DELTA t CRETE 20-LI	2000°F	38	1.0	1.2	1.4
DELTA t CRETE 20	2000°F	56	1.4	1.5	1.7
DELTA t CRETE 20-M	2100°F	67	2.1	2.3	2.7
DELTA t CRETE 22-LI	2200°F	51	1.3	1.7	2.0
DELTA t CRETE 22	2200°F	60	1.4	1.7	1.9
DELTA t CRETE 23-M	2300°F	80	2.3	2.5	2.8
DELTA t CRETE 23-M-LI	2300°F	76	2.1	2.4	2.7
DELTA t CRETE 25	2500°F	54	1.4	1.9	2.3
DELTA t CRETE 26-LI	2600°F	54	1.4	1.9	2.3
DELTA t CRETE 26-M	2600°F	81	2.4	2.6	3.0
DELTA t CRETE 26-M GUN MIX	2600°F	86	2.4	2.6	3.0
DELTA t CRETE 28	2800°F	89	3.1	3.6	4.8
DELTA t CRETE 30	3000°F	91	3.0	3.6	5.8
DELTA t CRETE 30 GUN MIX	3000°F	96	3.0	3.6	5.8
DELTA t CRETE 33	3300°F	98	6.1	5.0	5.2



*Manufacturing
Refractory Materials*

call toll free: (800) 437-6777
email: info@mtsavage.com