

# Red Low Duty

## Mt. Savage Specialty Refractories

736 West Ingomar Road

Ingomar, PA 15127

Tel: (412) 367-9100 • Fax: (412) 367-2228

## Product Data

### Scope:

Power pressed, to insure dense, strong brick.

Designed to satisfy general use where low temperatures are present and non-severe conditions exist.

**PCE:** 14—15

<u>CLASSIFICATION:</u>	ASTM C-27
<u>METHOD OF MANUFACTURE</u>	Dry Press
<u>MODULUS OF RUPTURE—PSI</u>	650—950
<u>APPARENT POROSITY %</u>	18—21
<u>COLD CRUSHING P. S. I.</u>	3500—4500
<u>BULK DENSITY—lbs/cu ft.</u>	130—132
<u>A.S.G.</u>	2.64

The data given above are average results-of our common sized products and are subject to variation. These results should not be used for specification purposes.

M299/01/06